



## FIRECLAY MORTARS

Type	Al <sub>2</sub> O <sub>3</sub> + TiO <sub>2</sub> , %	Refractoriness, °C	Humidity, %	Residue on sieve 0.5 mm, %
MSH 36	36	1730	5	< 5
MSH 30	30	1710	5	

## FIRECLAY FRACTIONS

Grain size	0 ÷ 1mm	0 ÷ 3mm	0 ÷ 5mm	1 ÷ 3mm	3 ÷ 5mm
------------	---------	---------	---------	---------	---------

Type	Al <sub>2</sub> O <sub>3</sub> + TiO <sub>2</sub> , %	Refractoriness, °C	Humidity, %
SHF 40	40	1730	3
SHF 36	36	1730	3
SHF 32	32	1710	3
SHF 28	28	1670	3

*TRUD JSC produce and some other grain sizes, as per customer specification.*